
8108269/DB | M-002-MN-8W-F02NS/109



LightScope ZWP® Self-Supporting Non-Armored Figure-8 Outdoor Drop Cable, 1–6 fiber Arid Core construction with 0.109 in messenger, central loose tube

Product Classification


PortfolioCommScope®Product TypeFiber drop cable

Regional Availability Asia | Australia/New Zealand | EMEA | Latin America | North America

Standards And Qualifications

Cable Qualification Standards ANSI/ICEA S-110-717

Representative Image



General Specifications

Cable TypeCentral loose tubeConstruction TypeNon-armoredSubunit TypeGel-filled

Construction Materials

Fiber Type Solution G.652.D and G.657.A1

Jacket Material PE

page 1 of 5 September 19, 2019



8108269/DB | M-002-MN-8W-F02NS/109

Total Fiber Count 2

Fiber Type G.652.D and G.657.A1

Fiber Type, quantity 2
Fibers per Subunit, quantity 2
Jacket Color Black

Jacket UV Resistance UV stabilized

Dimensions

Buffer Tube/Subunit Diameter 2.50 mm | 0.10 in
Cable Weight 77.0 kg/km | 52.0 lb/kft
Diameter Over Jacket 5.10 mm | 0.20 in
Diameter Over Messenger Jacket 4.30 mm | 0.17 in
Height Over Jacket 10.70 mm | 0.42 in

Subunit, quantity 1

Physical Specifications

Minimum Bend Radius, loaded 7.7 cm | 3.0 in

Minimum Bend Radius, unloaded 5.1 cm | 2.0 in

Tensile Load, long term, maximum 400 N | 90 lbf

Tensile Load, short term, maximum 1334 N | 300 lbf

Vertical Rise, maximum 529.0 m | 1736.0 ft

Environmental Specifications

Environmental Space Aerial, self-support

Installation Temperature $-30 \degree \text{C}$ to $+70 \degree \text{C}$ (-22 °F to $+158 \degree \text{F}$)

Operating Temperature $-40 \degree \text{C}$ to $+70 \degree \text{C}$ (-40 °F to $+158 \degree \text{F}$)

Storage Temperature $-40 \degree \text{C}$ to $+75 \degree \text{C}$ (-40 °F to $+167 \degree \text{F}$)

Mechanical Test Specifications

 Compression
 10 N/mm | 57 lb/in

 Compression Test Method
 FOTP-41 | IEC 60794-1 E3

Flex 35 cycles

 Flex Test Method
 FOTP-104
 IEC 60794-1 E6

 Impact
 1.47 N-m
 1.08 ft lb

Impact Test Method FOTP-25 | IEC 60794-1 E4

Strain See long and short term tensile loads

Strain Test Method FOTP-33 | IEC 60794-1 E1

Twist 10 cycles

Twist Test Method FOTP-85 | IEC 60794-1 E7

page 2 of 5 September 19, 2019



8108269/DB | M-002-MN-8W-F02NS/109

Water Penentration 24 h

Water Penentration Test Method FOTP-82 | IEC 60794-1 F5

Environmental Test Specifications

Cable Freeze -2 °C | 28 °F

Cable Freeze Test Method FOTP-98 | IEC 60794-1 F15

Drip 70 °C | 158 °F

Drip Test Method FOTP-81 | IEC 60794-1 E14 **Heat Age** -40 °C to +85 °C (-40 °F to +185 °F)

Heat Age Test Method IEC 60794-1 F9

Low High Bend-30 °C to +60 °C (-22 °F to +140 °F)Low High Bend Test MethodFOTP-37 | IEC 60794-1 E11Temperature Cycle-40 °C to +70 °C (-40 °F to +158 °F)

Temperature Cycle Test Method FOTP-3 | IEC 60794-1 F1

Regulatory Compliance/Certifications

Agency Classification ROHS 2011/65/EU Compliant

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system





Included Products

DB-8W-LT (Product Component—not orderable) — LightScope ZWP® Singlemode Fiber

* Footnotes

Operating Temperature Specification applicable to non-terminated bulk fiber cable



page 3 of 5



DB-8W-LT | DB-8W-LT

LightScope® 2000

LightScope ZWP® Singlemode Fiber

Product Classification

 Portfolio
 CommScope®

 Product Type
 Optical fiber

Regional Availability Asia | Australia/New Zealand | EMEA | Latin America | North

America

Optical Specifications, Wavelength Specific

Standards Compliance ITU-T G.652.D | ITU-T G.657.A1 | TIA-492CAAB (OS2)

Attenuation, maximum 0.22 dB/km @ 1,550 nm | 0.23 dB/km @ 1,575 nm | 0.25 dB/km

@ 1,490 nm | 0.25 dB/km @ 1,625 nm | 0.31 dB/km @ 1,385

nm | 0.35 dB/km @ 1,650 nm

Dispersion, maximum 18 ps(nm-km) at 1550 nm | 3.5 ps(nm-km) from 1285 nm to 1330

nm at 1310 nm

 Mode Field Diameter
 $10.4 \mu m$ @ 1,550 nm | 9.2 μm @ 1,310 nm | 9.6 μm @ 1,385 nm

 Mode Field Diameter Tolerance
 $\pm 0.3 \mu m$ @ 1310 nm | $\pm 0.5 \mu m$ @ 1550 nm | $\pm 0.6 \mu m$ @ 1385 nm

Index of Refraction 1.467 @ 1,310 nm | 1.468 @ 1,385 nm | 1.468 @ 1,550 nm

Polarization Mode Dispersion Link Design Value, maximum 0.04 ps/sqrt(km)

Backscatter Coefficient -79.6 dB @ 1,310 nm | -82.1 dB @ 1,550 nm

Physical Specifications

Cladding Diameter 125.0 µm **Cladding Diameter Tolerance** ±0.7 µm Cladding Non-Circularity, maximum 0.7 % **Coating Diameter (Colored)** 253 µm Coating Diameter (Uncolored) 240 µm Coating Diameter Tolerance (Colored) ±7 µm **Coating Diameter Tolerance (Uncolored)** ±5 µm Coating/Cladding Concentricity Error, maximum 12 µm Core/Clad Offset, maximum 0.5 µm

Optical Specifications, General

Cabled Cutoff Wavelength, maximum1260 nmPoint Defects, maximum0.10 dB

Zero Dispersion Slope, maximum 0.090 ps/[km-nm-nm]

Zero Dispersion Wavelength, maximum1322 nmZero Dispersion Wavelength, minimum1302 nm

Mechanical Specifications

page 4 of 5 September 19, 2019



DB-8W-LT | DB-8W-LT

8.9 N | 2.0 lbf Coating Strip Force, maximum 1.3 N | 0.3 lbf Coating Strip Force, minimum

Dynamic Fatigue Parameter, minimum 20

Fiber Curl, minimum 4.0 m | 13.1 ft

Macrobending, 20 mm mandrel, 1 turn 0.75 dB @ 1,550 nm | 1.50 dB @ 1,625 nm 0.25 dB @ 1,550 nm | 1.00 dB @ 1,625 nm Macrobending, 30 mm mandrel, 10 turns Macrobending, 50 mm mandrel, 100 turns 0.03 dB @ 1,550 nm | 0.03 dB @ 1,625 nm

Proof Test 689.48 N/mm² | 100000.00 psi

Environmental Specifications

0.05 dB/km @ 85 °C Heat Aging, maximum

Temperature Dependence, maximum 0.05 dB/km Temperature Humidity Cycling, maximum 0.05 dB/km

Water Immersion, maximum 0.05 dB/km @ 23 °C

Regulatory Compliance/Certifications

Classification Agency

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system



* Footnotes

Temperature dependence is conducted at -60 °C to +85 °C (-76 °F to +185 °F) Temperature Dependence, maximum

Temperature Humidity Cycling, maximum Temperature humidity cycling is conducted at -10 °C to +85 °C (+14 °F to +185 °F) up to

95% relative humidity

