



Toneable ConQuest® Empty Conduit, 2 in, SCH 40, black, with pull tape

## Product Classification

<b>Product Type</b>	Empty conduit
<b>Product Brand</b>	ConQuest®

## General Specifications

<b>Color</b>	Black
<b>Conductor Elongation, maximum</b>	30 %
<b>Conductor Type</b>	Solid
<b>Conduit Type</b>	Toneable
<b>Density Test Method</b>	ASTM D792A
<b>Density, maximum</b>	0.955 g/cm <sup>3</sup>   0.035 lb/in <sup>3</sup>
<b>Density, minimum</b>	0.941 g/cm <sup>3</sup>   0.034 lb/in <sup>3</sup>
<b>Design Standard</b>	ASTM D3350-05
<b>Wall Type</b>	Smooth

## Dimensions

<b>Length</b>	762 m   2500 ft
<b>Conductor Diameter</b>	1.024 mm   0.04 in
<b>Inner Diameter, nominal</b>	51.994 mm   2.047 in
<b>Outer Diameter, nominal</b>	60.325 mm   2.375 in
<b>Wall Thickness Designation</b>	SCH 40
<b>Wall Thickness, minimum</b>	3.912 mm   0.154 in
<b>Nominal Size</b>	2 in
<b>Conductor Gauge</b>	18 AWG

## Electrical Specifications

<b>Conductor Resistance</b>	98.425 ohms/km   30 ohms/kft
-----------------------------	------------------------------

# 3799159 | 200B(TD)040 WP1250TAPE

---

## Material Specifications

<b>Conductor Material Type</b>	Copper-clad steel (CCS)
<b>Flexural Modulus, minimum</b>	551.581 N/mm <sup>2</sup>   80000 psi
<b>Flexural Property Test Method</b>	ASTM D790
<b>Hydrostatic Design Basis</b>	Not pressure rated
<b>Hydrostatic Design Test Method</b>	ASTM D2837
<b>Material Type</b>	High density polyethylene (HDPE)   Polyester
<b>Melt Flow Rate Test Method</b>	ASTM D1238
<b>Melt Flow Rate, maximum</b>	0.39 g/10 min

## Mechanical Specifications

<b>Minimum Bend Radius, unsupported</b>	660.4 mm   26 in
<b>Tensile Property Test Method</b>	ASTM D638
<b>Tensile Strength at yield, minimum</b>	20.684 N/mm <sup>2</sup>   3000 psi
<b>Breaking Strength</b>	566.99 kg   1250 lb
<b>Conductor Tensile Strength, minimum</b>	344.738 N/mm <sup>2</sup>   50000 psi
<b>Pull Line Type</b>	Tape
<b>Pulling Tension Note</b>	Applies to products manufactured after December 31, 2012
<b>Pulling Tension, maximum</b>	1,043.262 kg   2300 lb

## Environmental Specifications

<b>Environmental Stress Crack Resistance</b>	Failure rate of 10% within 96 hours
<b>Environmental Stress Test Method</b>	ASTM D1693, ESCR Condition B

## Packaging and Weights

<b>Weight, net</b>	702.413 kg/km   472 lb/kft
--------------------	----------------------------

## Regulatory Compliance/Certifications

<b>Agency</b>	<b>Classification</b>
ISO 9001:2015	Designed, manufactured and/or distributed under this quality management system

## \* Footnotes

**Environmental Stress Crack Resistance** ESCR—Environmental Stress Crack Resistance