CX3299999 | 100T135 EMPTY DUCT COEX



ConQuest® Empty Conduit, 1 in, SDR 13.5, terracotta

 *Product complies with the Build America, Buy America Act (BABAA) requirements of the Infrastructure Investment and Jobs Act of 2021 (Pub. L. 117- 58, §§ 70901-70953), or is the subject of a waiver approved by the Secretary of Commerce or designee. Compliance requirements and waiver applicability vary based on government funding program. Check the laws and regulations for your specific program.

Product Classification

Regional AvailabilityNorth AmericaProduct TypeEmpty conduitProduct BrandConQuest®

Government Funding Build America Buy America (BABA) compliant*

General Specifications

ColorTerracottaConduit TypeNon-toneableDensity Test MethodASTM D792A

 Density, maximum
 0.955 g/cm³ | 0.035 lb/in³

 Density, minimum
 0.941 g/cm³ | 0.034 lb/in³

Design Standard ASTM D3350-05

Wall Type Smooth

Dimensions

Length 914.4 m | 3000 ft

Inner Diameter, nominal27.965 mm | 1.101 inOuter Diameter, nominal33.401 mm | 1.315 in

Wall Thickness Designation SDR 13.5

Wall Thickness, minimum 2.464 mm | 0.097 in

Nominal Size 1 in

Material Specifications

Flexural Modulus, minimum 551.581 N/mm² | 80000 psi

Flexural Property Test Method ASTM D790

COMMSCOPE®

CX3299999 | 100T135 EMPTY DUCT COEX

Hydrostatic Design BasisNot pressure rated

Hydrostatic Design Test MethodASTM D2837

Material Type High density polyethylene (HDPE)

Melt Flow Rate Test MethodASTM D1238Melt Flow Rate, maximum0.39 g/10 min

Mechanical Specifications

Minimum Bend Radius, unsupported 355.6 mm | 14 in

Tensile Property Test MethodASTM D638

Tensile Strength at yield, minimum 20.684 N/mm² | 3000 psi

Pulling Tension, maximum 358.338 kg | 790 lb

Environmental Specifications

Environmental Stress Crack Resistance Failure rate of 10% within 96 hours
Environmental Stress Test Method ASTM D1693, ESCR Condition B

Packaging and Weights

Weight, net 251.5 kg/km | 169 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system



* Footnotes

Environmental Stress Crack Resistance ESCR—Environmental Stress Crack Resistence

