## CX3799717 | 200T110WP1800TAPE COEX



## ConQuest® Empty Conduit, 2 in, SDR 11, terracotta, with pull tape

 \*Product complies with the Build America, Buy America Act (BABAA) requirements of the Infrastructure Investment and Jobs Act of 2021 (Pub. L. 117- 58, §§ 70901-70953), or is the subject of a waiver approved by the Secretary of Commerce or designee. Compliance requirements and waiver applicability vary based on government funding program. Check the laws and regulations for your specific program.

#### **Product Classification**

Regional AvailabilityNorth AmericaProduct TypeEmpty conduitProduct BrandConQuest®

**Government Funding**Build America Buy America (BABA) compliant\*

#### General Specifications

ColorTerracottaConduit TypeNon-toneableDensity Test MethodASTM D792A

 Density, maximum
 0.955 g/cm³ | 0.035 lb/in³

 Density, minimum
 0.941 g/cm³ | 0.034 lb/in³

**Design Standard** ASTM D3350-05

Wall Type Smooth

#### **Dimensions**

**Length** 762 m | 2500 ft

 Inner Diameter, nominal
 48.692 mm | 1.917 in

 Outer Diameter, nominal
 60.325 mm | 2.375 in

Wall Thickness Designation SDR 11

**Wall Thickness, minimum** 5.486 mm | 0.216 in

Nominal Size 2 in

Material Specifications

**Flexural Modulus, minimum** 551.581 N/mm² | 80000 psi

Flexural Property Test Method ASTM D790

**COMMSCOPE®** 

# CX3799717 | 200T110WP1800TAPE COEX

**Hydrostatic Design Basis**Not pressure rated

**Hydrostatic Design Test Method**ASTM D2837

Material Type High density polyethylene (HDPE) | Polyester

Melt Flow Rate Test MethodASTM D1238Melt Flow Rate, maximum0.39 g/10 min

Mechanical Specifications

Minimum Bend Radius, unsupported 660.4 mm | 26 in

Tensile Property Test Method ASTM D638

**Tensile Strength at yield, minimum** 20.684 N/mm<sup>2</sup> | 3000 psi

**Breaking Strength** 816.466 kg | 1800 lb

Pull Line Type Tape

**Pulling Tension, maximum** 1,408.404 kg | 3105 lb

**Environmental Specifications** 

**Environmental Stress Crack Resistance** Failure rate of 10% within 96 hours

**Environmental Stress Test Method**ASTM D1693, ESCR Condition B

Packaging and Weights

**Weight, net** 952.425 kg/km | 640 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system



### \* Footnotes

**Environmental Stress Crack Resistance** ESCR—Environmental Stress Crack Resistence

